

**Product Name: E 657 Provisional**

**PVC Coated tarp**

**End Use:** KEDER, Light Weight Membrane

Properties	Typical Characteristics	
Test & Method	English	Metric
Base Fabric	Polyester 1,000 Den 8.1 [Oz/yd <sup>2</sup> ]	Polyester 1,100 Dtx 275 [gr/m <sup>2</sup> ]
Total Weight ASTM D 751	19.2 [Oz/yd <sup>2</sup> ]	650 [gr/m <sup>2</sup> ]
Breaking Strength - Strip ASTM D 751 method B	500 / 500 [lbs/inch]	4500 / 4500 [N/5 cm]
Tear Strength - Single Rip ASTM D 751 method B, DIN 53356	275 / 243 [lbs]	1250 / 1100 [N]
Coating Adhesion (HF Welding) ASTM D 751	22 / 22 [lbs/inch]	200 / 200 [N/5 cm]