

Product Name: E 760
PVC coated one side tarp
End Use: KEDER fabric

Properties	Typical Characteristics	
Test & Method	English	Metric
Base Fabric	Polyester 1,500 Den 14.7 [Oz/yd ²]	Polyester 1,670 Dtx 500 [gr/m ²]
Total Weight ASTM D 751	22.3 [Oz/yd ²]	760 [gr/m ²]
Breaking Strength - Strip ASTM D 751 method B	815 / 715 [lbs/inch]	7300 / 6400 [N/5 cm]
Tear Strength - Single Rip ASTM D 751 method B, DIN 53356	220 / 220 [lbs]	1000 / 1000 [N]
Tear Strength - Double Rip ISO 4674	350 / 330 [lbs]	1600 / 1500 [N]
Tear Strength - Trapez DIN 53363	265 / 240 [lbs]	1200 / 1100 [N]
Adhesion (HF Welding) ASTM D 751	13 / 13 [lbs/inch]	120 / 120 [N/5 cm]
Flex Resistance DIN 53359 A	Min. 100,000 cycles	
Flame Resistance DIN 5433	2.7 inch/min	70 mm/min
Cold Crack / Bend DIN 53361	-22°F	-30°C

Comments: Preliminary specification based upon initial production run.