



Revision Date: 10/21/2019

Approved by: RR

Version: TL-0

## PRODUCT SPECIFICATION

PRODUCT ID # : 9234-30120-559

EPT Xtrm Ply PW White 9234 - 30 oz NSF 61

### Base Fabric

Weight 2.6 oz/yd<sup>2</sup> (88 g/m<sup>2</sup>)  
Yarn Polyester

### Coating

Polymer EIA/KEE  
Color White  
Sealing RF, Hot Air, Wedge  
Width 60.0 in 120 in

Physical Properties	Units	Test Method	Minimum value	
Thickness (typical)	mils	ASTM D751	34.0 (± 5%)	
	mm		0.86	
Weight (typical)	oz/yd <sup>2</sup>	ASTM D751	30	
	g/m <sup>2</sup>		1017	
Tear Strength	lbs	ASTM D751- B	35 (MD)	35 (TD)
(Tongue Tear)	N		156 (MD)	156 (TD)
Breaking Strength	lbs	ASTM D751-A	175 (MD)	175 (TD)
(Grab Tensile)	N		778 (MD)	778 (TD)
Adhesion- Ply	lb/in	ASTM D751	10	
	N/25mm		44	
Low Temperature Bend Test (1/8" Mandrel, 4 hours)	°F	ASTM D2136	-25	
	°C		-32	
Dimensional Stability (max)	%	ASTM D1204	3.0%	

This product conforms with NSF/ANSI 61 Drinking water system components - Protective Barrier Materials ( ≥ 5 gal.)

Product Specifications are minimum values, actual results may be higher

*We believe this information is the best currently available on the subject. It is provided as a suggestion in any appropriate experimentation you may care to undertake. It is subject to revision as additional knowledge, information and experience are gained. We make no guarantee of results and assume no obligation, warranty or liability whatsoever in connection with this information. In case of conflict between standard and metric specifications, standard shall apply*