



**Erez Thermoplastic Products** Kibbutz Erez M.P Ashkelon Coast 7915000 Israel Tel: +972 8 6801200 / 201 | sales\_etp@erez-therm.com www.erez-therm.com

Product Name: GlowSpot® U1001

Retro-Reflective Polyurethane coated membrane, Nylon fabric.

End Use: Inflatable life jacket bladders.

Certified in accord to: UL 1191 File No. MQ1807 - Codes 1F, 2F, 3F, 5H and ISO 12402-7

Properties	Typical Characteristics	
Test & Method	English	Metric
Fabric Type	Nylon HT 210 Den	Nylon HT 235 Dtx
Fabric Count	66 / 56 per inch	26 / 22 per cm
ASTM D 3775		•
Width[s]**	59, 81 [inches]	150, 205 [cm]
Total Weight	8.2 [Oz/yd²]	280 [gr/m²]
ASTM D 751 / ISO 3801	. ,, .	10 / 1
Tensile Strength	292 / 270 [lbs]	1300 / 1200 [N]
ISO 13934 – 2	> 000/	
After acc. Ageing 168 hrs @ 70 °C (158 °F)	≥ 90%	
Breaking Strength ASTM D 5034	292 / 270 [lbs]	1300 / 1200 [N]
After acc. Ageing 168 hrs @ 70 °C (158 °F)	≥ 90%	
Tear strength - Trapez		
ISO 9073 – 4	12.3 / 10.1 [lbs]	55 / 45 [N]
After acc. Ageing 168 hrs @ 70 °C (158 °F)	≥ 90%	
Trapezoid Tear Strength	≥ 10 / 8 [lbs]	≥ 45 / 36 [N]
FTMS 191A Method 5136	2 10 / 0 [lb3]	2 43 / 30 [N]
After acc. Aging 168 hrs @ 70 °C (158 °F)	≥ 90%	
FTMS 191A Method 5850	_55%	
Permeability of CO <sub>2</sub>	< 0.7 [dm³/(day*m²)]	
ISO 7229	≤ 110%	
After acc. Ageing 168 hrs @ 70 °C (158 °F) After 360 hrs @ 65°C (149 °F) & 95% R.H.	≤ 110% ≤ 110%	
Permeability of CO <sub>2</sub>	_	
ASTM D1434	1.25x10 <sup>-13</sup> [mol /m².s.Pa]	
After acc. Ageing 168 hrs @ 70 °C (158 °F)	≤ 110%	
After 360 hrs @ 65°C (149°F) & 95% R.H.	≤ 110%	
Coating Adhesion (HF Welding)		
ISO 2411	78 / 78 [lbs/inch]	700 / 700 [N/50 mm]
After 42 days at 70°C over water	73 / 73 [lbs/inch]	650 / 650 [N/50 mm]





**Erez Thermoplastic Products** | Kibbutz Erez M.P Ashkelon Coast 7915000 Israel Tel: +972 8 6801200 / 201 | sales\_etp@erez-therm.com www.erez-therm.com

Seal Seam Strength ASTM F88 & ASTM D5035 Method 2C-E	≥ 65 / 65 [lbs/inch]	≥ 114 / 114 [N/cm]
After exp. 360 hrs @ 149°F (65°C) & 95% R.H.	≥ 75%	
Resistance to flex cracking	No damage	
(9000 cycles)		
ISO 7854 Method A		
After 42 days @70 °C (158 °F) over water	No damage	

<sup>\*\*</sup> For special/additional widths, please contact EREZ's representative.

**PROP 65:** The product does not require warning label in accord to proposition 65:2018, as the product does not contain a listed substance or/and is under the NSRL "Safe Harbor" levels.